

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**

THIS PAGE BLANK (USPTO)

374/257



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C06D 5/06, C06B 25/34, C01B 21/82		A1	(11) International Publication Number: WO 98/55428
			(43) International Publication Date: 10 December 1998 (10.12.98)
(21) International Application Number: PCT/SE98/00949 (22) International Filing Date: 20 May 1998 (20.05.98) (30) Priority Data: 9701897-2 21 May 1997 (21.05.97) SE (71) Applicant (for all designated States except US): FÖRSVARETS FORSKNINGSSANSTALT [SE/SE]; S-172 90 Stockholm (SE). (72) Inventor; and (75) Inventor/Applicant (for US only): LANGLET, Abraham [SE/SE]; Surbrunnsgatan 33, S-113 48 Stockholm (SE). (74) Agent: FÖRSVARETS MATERIELVERK; Patentenheten, S-115 88 Stockholm (SE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report. In English translation (filed in Swedish).	
(54) Title: NEW CHEMICAL COMPOUND, EXPLOSIVE CONTAINING THE COMPOUND AND USE OF THE COMPOUND IN GAS GENERATORS <div style="text-align: center;"> <p>(I)</p> </div>			
(57) Abstract The invention relates to a new chemical compound suitable for use as an explosive and consisting of guanyldurea dinitramide having formula (I). The invention also concerns explosives, especially propellants, containing the compound; a pressed rocket motor charge containing the compound as the main component, and use of the compound as a gas-generating compound in gas generators for vehicle safety equipment such as airbags.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakistan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

New Chemical Compound, Explosive Containing the Compound and Use of the Compound in Gas Generators

5 The invention relates to a new compound suitable for use as an explosive. More specifically, the invention concerns a new dinitramide salt. The salt can be used as a high explosive, propellant or gas-generating compound in gas generators in pure form or as a component in explosive compositions.

10 The preparation of dinitramide salts such as ADN (ammonium dinitramide) and KDN (potassium dinitramide) is disclosed in, for instance, WO 91/19669, WO 91/19670, WO 93/16002 and WO 97/06099. These dinitramide salts are in the first place intended to be used as oxidisers, e.g. to replace ammonium perchlorate, in explosive compositions. The absence of chlorine is advantageous from the viewpoint of air pollution and in military applications owing to a decreased exhaust gas signature.


15 An object of the present invention is to provide a compound which is suitable as an explosive and which contains the dinitramide ion and has low solubility in water and low impact and friction sensitivity.

20 A further object of the invention is to provide a homogeneous propellant which contains the dinitramide ion and which has good pressing properties.

25 One more object of the invention is to provide a compound which is suitable as a gas-generating compound in gas generators for vehicle safety equipment such as airbags.

The invention is defined in the claims.

30 According to the invention the compound consists of guanylurea dinitramide having the formula



in the following referred to as GUDN.

The invention also concerns an explosive containing the compound; a propellant containing the compound; a pressed rocket motor charge containing the compound as the main component, and use of the compound as a gas-generating compound in gas generators for vehicles safety equipment such as airbags.

GUDN is a white crystalline powder which has low solubility in water, has no melting point and has a decomposition temperature of about 180°C. The crystal size may vary according to the conditions of preparation. The powder is pressable and can be pressed to, for instance, propellant grains and rocket motor charges of different shape. The burning properties are favourable. The burning rate is high and linearly dependent on the pressure and the formed combustion gases are light. GUDN is highly insensitive to impact and friction. When testing the impact sensitivity in a BAM fall hammer with a fall weight of 2 kg, the compound was not initiated even if the fall height was increased to 2 m. For comparison, it may be mentioned that RDX at a corresponding fall weight is initiated at a fall height of 38 cm. The friction sensitivity could not be tested in a normal Julius Peter friction tester since the compound was not initiated within the capacity range of the tester (36 kp pistil load).

GUDN can be made to detonate and then has a detonation velocity that can be compared to RDX. The compound can thus be used as a high explosive in pure form or as a component in explosive compositions. In many applications where explosives are used, binder systems and preparation methods have been developed for explosives which are not water-soluble, such as HMX and RDX. GUDN can be used in such binder systems and preparation methods and replace previously used explosives.

GUDN can be used as a propellant alone or as a component in propellant compositions and can, in many applications, replace e.g. nitramine propellant, composite propellant and nitrocellulose propellant. The stability is better than for NC propellant and composite propellant and the burning rate is higher than for nitramine propellant. GUDN produces considerably lighter combustion gases than e.g. an NC propellant, which is advantageous in projectile propellant charges when higher muzzle velocities are desired. This is the case, for instance, with shotgun ammunition when steel pellets are used instead of the considerably heavier lead pellets. Propellants based on GUDN can thus have great advantages in a number of applications in which NC propellants are currently predominant.

GUDN has suitable properties for use as a rocket propellant and, owing to the excellent pressing properties, pressed rocket motor charges can be prepared, containing GUDN as the main component. A small amount of binder, e.g. a polymer, can be used to increase the pressability and the strength of the compact, but for many applications, sufficient strength can be achieved without the addition of a binder.

Especially for rockets such as emergency rockets and the like, which at regular intervals are exchanged and scrapped, a pressed motor charge of GUDN gives great advantages. In emergency rockets, use is in most cases made of propellant charges consisting of ammonium perchlorate and a polymeric binder, for instance, a phenol resin, which is cured to a cross-linked structure. The reliability of an emergency rocket decreases in course of time and the rocket must therefore be replaced at regular intervals. The motor absorbs, among other things, moisture since ammonium perchlorate is hygroscopic. Upon replacement, the old rocket is returned to the manufacturer and the rocket motor charge is destroyed (burnt).

GUDN is non-hygroscopic and offers even in this respect an advantage relative to propellant charges containing ammonium perchlorate. GUDN has very low solubility in cold water and moderate solubility in hot water. A pressed charge consisting of GUDN as the main component can therefore be scrapped by being dissolved with hot water as solvent, and pure GUDN can be recrystallised from the aqueous solution and be reused. An environmentally acceptable scrapping of the rocket motor charge and reuse of the propellant can thus be achieved.

Moreover, the compound is fully soluble in ADN and can be used as an additive to ADN in, for instance, rocket propellants for decreasing the burning exponent.

Another very advantageous field of application for GUDN is the use as a gas-generating compound in gas generators for vehicle safety equipment such as airbags and the like. In the same manner as for emergency rockets, the possibility of environmentally acceptable recovery of the gas-generating compound is essential to these gas generators. In gas generators for airbags and the like, use is today made of compositions containing azides, composite propellant, NC propellant and nitramine propellant, which all have advantages and disadvantages. Azides are noxious; composite propellant contains chlorine, which generates noxious combustion

gases, inter alia, dioxins and HCl; NC propellant causes problems with the long-term stability; nitramine propellant does not generate noxious gases but has a low burning rate and the combustion is difficult to catalyse.

- 5 GUDN has all advantages and generates no noxious gases, has good stability and a burning rate which is comparable to NC propellant.

The low solubility of the compound in water makes it easy to prepare by a precipitation reaction from an aqueous solution. An aqueous solution of a guanylurea salt,
10 e.g. guanylurea sulphate, is reacted with a water-soluble dinitramide salt, thereby forming a precipitate of guanylurea dinitramide.

Suitable guanylurea salts that can be used in the preparation are those that can be dissolved in water. A certain acidification of the water may be required to make the
15 salt dissolve.

Suitable dinitramide salts that can be used in the preparation are, for instance, ADN, KDN and other water-soluble dinitramide salts, which are selected in consideration of the condition that the positive ion should not form an additional precipitate
20 which makes the extraction of the guanylurea dinitramide difficult.

The invention will be described below by way of Examples.

Example 1.

25

Solution 1:

3.2 g of guanylurea sulphate were dissolved in 15 ml of water after adjusting the pH to 5-7 by dripping diluted sulphuric acid into the water. A clear solution was obtained.

30

Solution 2:

2.5 g of ADN were dissolved in 3 ml of water.

Solution 1 was added to solution 2, thereby forming a precipitate. The precipitate
35 was filtered off and washed with water. 3.4 g of guanylurea dinitramide were obtained as a fine white powder.

The powder was pressed to pellets and the burning properties were tested in a burning chamber (minibomb). A measured pressure/time curve from the combustion is shown in Fig. 1, and Fig. 2 shows the burning rate as a function of pressure. The burning rate was linearly dependent on the pressure and generally comparable to
5 an NC propellant.

Example 2.

Solution 1:

10 3.2 g of guanylurea sulphate were dissolved in 30 ml of water in the same way as in Example 1.

Solution 2:

2.5 g of ADN were dissolved in 30 ml of water.

15

Both solutions were heated to 40°C and mixed. The product crystallised slowly when cooling the mixture. The crystals were filtered off and washed with water. 3.2 g of guanylurea dinitramide were obtained in the form of white crystals. In this case the crystals were considerably larger than in the product of Example 1.

20

In a manner corresponding to that described in Examples 1 and 2, the product can be prepared by using KDN or some other water-soluble dinitramide salt. It is also possible to prepare guanylurea dinitramide in direct connection with the preparation of the dinitramide salt. For instance WO 97/06099 discloses how dinitramide salt is
25 prepared by neutralisation of dinitramide acid prepared by nitration. A guanylurea salt can be added directly to this mixture without first isolating the dinitramide salt. A certain coprecipitation of nitrates, however, may arise.


Example 3.

30

A fine powder of GUDN was pressed to a charge with the dimensions 30 mm diameter and 2 mm height. The charge was extracted with boiling water in a Soxhlet extraction apparatus. The charge was completely dissolved and GUDN recrystallised in the flask. A new charge could be pressed from the recrystallised substance.

Claims:

1. A compound suitable for use as an explosive, characterised in that it consists of
5 guanylurea dinitramide having the formula



2. An explosive, characterised in that it contains guanylurea dinitramide.
3. A propellant, characterised in that it contains guanylurea dinitramide.
- 15 4. A pressed rocket motor charge, characterised in that it contains guanylurea dinitramide as the main component.
5. Use of guanylurea dinitramide as a gas-generating compound in gas generators
20 for vehicle safety equipment such as airbags.

1/1




Fig 1




Fig 2

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 98/00949

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C06D 5/06, C06B 25/34, C01B 21/82
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C01B, C06B, C06D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

STN: REG. CA, QUESTEL: WPIL

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0519485 A1 (DYNAMIT NOBEL AKTIENGESELLSCHAFT), 23 December 1992 (23.12.92), page 1, line 1 - line 5; page 1, line 15 - line 17; page 3, line 15 - line 18 --	1-5
A	WO 9626169 A1 (DYNAMIT NOBEL AKTIENGESELLSCHAFT), 29 August 1996 (29.08.96), claims 1-2 --	1-5
A	EP 0607446 A1 (NIPPON KOKI CO., LTD.), 27 July 1994 (27.07.94), page 3, line 37 - line 43 --	1-5
A	US 3758555 A (ROBERT J. KOSCHAR ET AL), 11 Sept 1973 (11.09.73), column 4, line 27 - line 43 --	1-5

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

24 August 1998

Date of mailing of the international search report

28-08-1998

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Bengt Christensson

Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 98/00949

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2953448 A (W.MAXWELL), 20 Sept 1960 (20.09.60), claim 1 -- -----	1-5

INTERNATIONAL SEARCH REPORT

Information on patent family members

27/07/98

International application No.

PCT/SE 98/00949

Patent document cited in search report			Publication date	Patent family member(s)		Publication date
EP	0519485	A1	23/12/92	DE	4220019 A	24/12/92
WO	9626169	A1	29/08/96	CA	2211579 A	29/08/96
				CZ	9702621 A	17/12/97
				DE	19505568 A	22/08/96
				EP	0809616 A	03/12/97
				PL	321832 A	22/12/97
EP	0607446	A1	27/07/94	CN	1083463 A	09/03/94
				JP	6032689 A	08/02/94
				WO	9401381 A	20/01/94
				JP	6032690 A	08/02/94
US	3758555	A	11/09/73	US	3927103 A	16/12/75
US	2953448	A	20/09/60	NONE		